

TEST REPORT

DATE: 07-31-2026

Page 1 of 1

TEST NUMBER: 0332175

CLIENT	Urban Surfaces
--------	----------------

TEST METHOD CONDUCTED	ASTM D2047 James Machine - Coefficient of Friction on Flooring Material
-----------------------	---

DESCRIPTION OF TEST SAMPLE	
IDENTIFICATION	FlexPC

PRINCIPLE


This test is used to measure the relative static coefficient of friction by using the James Machine.

TEST RESULTS

TEST ENVIRONMENT	72° F 50% Relative Humidity
------------------	-----------------------------

Sensor Materials	Dry
Leather	0.82

APPROVED BY: *Brandon Stokes*
Lab Director



This facility is accredited by the National Voluntary Laboratory Accreditation Program for the specific scope of accreditation under Lab Code 100297. This accreditation does not constitute an endorsement, certification, or approval by NIST or any agency of the United States Government for the product tested. This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical or similar products. This report, or the name of Professional Testing Laboratory, LLC, shall not be used under any circumstance in advertising to the general public.



Accreditation #93341