

TEST REPORT

DATE: 12-30-2024

Page 1 of 1

TEST NUMBER: 0313136

CLIENT	Urban Surfaces
--------	----------------

TEST METHOD CONDUCTED	ASTM D2047 James Machine - Coefficient of Friction on Flooring Material
-----------------------	---

DESCRIPTION OF TEST SAMPLE	
IDENTIFICATION	Sound-Tec Plus Modified Core
CONSTRUCTION	LSPC 4.5mm 20mil 9x60
BACKING	1.5mm EVA Pad

GENERAL PRINCIPLE

This test was used to measure the relative static coefficient of friction by using the James Machine.

TEST RESULTS

TEST ENVIRONMENT	69° F 50% Relative Humidity
------------------	-----------------------------

Sensor Materials	Dry
Standard Neolite	0.71
Leather	0.67

APPROVED BY:




This facility is accredited by the National Voluntary Laboratory Accreditation Program for the specific scope of accreditation under Lab Code 100297. This accreditation does not constitute an endorsement, certification, or approval by NIST or any agency of the United States Government for the product tested. This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical or similar products. This report, or the name of Professional Testing Laboratory, LLC, shall not be used under any circumstance in advertising to the general public.



Accreditation #93341