

TEST REPORT

DATE: 12-30-2024

Page 1 of 1

TEST NUMBER: 0313136

CLIENT	Urban Surfaces
--------	----------------

TEST METHOD CONDUCTED	ASTM F387 Standard Test Method for Measuring Thickness of Resilient Floor Covering with Foam Layer
-----------------------	--

DESCRIPTION OF TEST SAMPLE	
IDENTIFICATION	Sound-Tec Plus Modified Core
CONSTRUCTION	LSPC 4.5mm 20mil 9x60
BACKING	1.5mm EVA Pad

GENERAL PRINCIPLE

The total thickness of a resilient flooring material is determined through measurements made using a .250 inch presser foot and a dial micrometer. The average of 5 total measurements is reported as the average total thickness.

TEST RESULTS

SPECIMEN 1	0.245 inch
SPECIMEN 2	0.244 inch
SPECIMEN 3	0.245 inch
SPECIMEN 4	0.243 inch
SPECIMEN 5	0.242 inch

AVERAGE TOTAL THICKNESS	0.244 inch
-------------------------	------------

APPROVED BY:




This facility is accredited by the National Voluntary Laboratory Accreditation Program for the specific scope of accreditation under Lab Code 100297. This accreditation does not constitute an endorsement, certification, or approval by NIST or any agency of the United States Government for the product tested. This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical or similar products. This report, or the name of Professional Testing Laboratory, LLC, shall not be used under any circumstance in advertising to the general public.



Accreditation #93341