

TEST REPORT

DATE: 12-30-2024

Page 1 of 1

TEST NUMBER: 0313136

CLIENT	Urban Surfaces
--------	----------------

TEST METHOD CONDUCTED	ASTM F925 Standard Test Method for Resistance to Chemicals of Resilient Flooring
-----------------------	--

DESCRIPTION OF TEST SAMPLE	
IDENTIFICATION	Sound-Tec Plus Modified Core
CONSTRUCTION	LSPC 4.5mm 20mil 9x60
BACKING	1.5mm EVA Pad

GENERAL PRINCIPLE

This test method provides a procedure for determining the resistance of resilient floor covering to surface deterioration when exposed to various chemical reagents. This test method is not intended as a staining test nor as a method to judge surface and appearance restoration of the sample after exposure to the chemical reagent.

TEST RESULTS

5 MINUTE RATINGS				24 HOUR RATINGS		
STAINING AGENT	SURFACE DULLING	SURFACE ATTACK	COLOR CHANGE	SURFACE DULLING	SURFACE ATTACK	COLOR CHANGE
5% Acetic Acid	0	0	0	0	0	0
70% Isopropyl Alcohol	0	0	0	0	0	0
Mineral Oil	0	0	0	0	0	0
5% Sodium Hydroxide	0	0	0	0	0	0
5% Hydrochloric Acid	0	0	0	0	0	0
5% Ammonia	0	0	0	0	0	0
Bleach	0	0	0	0	0	0
5% Phenol	0	0	0	0	0	0
Gasoline	0	0	0	0	0	0
5% Sulfuric Acid	0	0	0	0	0	0
Kerosene	0	0	0	0	0	0
Olive Oil	0	0	0	0	0	0

RATING KEY	
0	No change (---)
1	Slight change
2	Moderate change
3	Severe change

APPROVED BY:



This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical or similar products.

This report, or the name of Professional Testing Laboratory, LLC, shall not be used under any circumstance in advertising to the general public.